

TECHNICAL DATA SHEET

ADSTET-N15D0600

Wood Natural Effect 1

High Performance Recycled PP Compound

Quality assured by AD Compound Material Managing Procedure



PHYSICAL	METHOD	UNITS	RANGE VALUE
MFI (E2) 190°C/10 Kg - [WPC]	ISO 1133	g/10min	>= 30,0
DENSITY 23°C	ISO 1183	g/cm3	0,970 ÷ 1,000
XRF (RoHS DIRECTIVE)	IDO 10 LAB		CONFORM
MECHANICAL	METHOD	UNITS	RANGE VALUE
TENSILE MODULUS (+23°C 2mm/min)	ISO 527	MPa	>= 1900
IMPACT	METHOD	UNITS	RANGE VALUE
CHARPY IMPACT STRENGTH, NOTCHED (+23°C)	ISO 179-1/1eA	kJ/ m²	>= 2,50
OTHER	METHOD	UNITS	RANGE VALUE
RECYCLE PLASTIC CONTENT	INTERNAL	%	>=70
CARBON FOOTPRINT REDUCTION²	INTERNAL	Kg CO₂ eq/kg	- 76%

RECOMMENDED PROCESSING CONDITIONS

DRYING TEMPERATURE (°C)	90
DRYING TIME (h)	2-4
MELT TEMPERATURE (°C)	180 - 200
INJECTION SPEED	Medium
INJECTION PRESSURE	Medium
SHOT WEIGHT\BARREL CAPACITY (%)¹	25-50

¹ Recommendation suggested before processing.

² Reduction of carbon footprint, based on raw materials formulation only, compared to a virgin matrix PP Compound 12% mineral filled. The calculation has been carried out internally based on data available on literature and considering at least 70% of PIR PP matrix.

- Using less than 25% of the barrel capacity will extend the amount of time in which material sits in the barrel and it could cause the degradation of material.

- Using more than 50% of the barrel capacity may not give material pellets the proper amount of time to melt and cause the material to have a non-uniform plasticization with the potential surface defects on the product.

Residence time on the same **barrels shot capacity** also depends on the cycle time which has to be correlated to the product and mould.

For the contact details of the A.D. COMPOUND S.p.a company selling this product in your country, please visit www.adcompound.com

The information contained herein is to our knowledge accurate and reliable as the date of publication. A.D. COMPOUND S.p.a extends no warranties and makes no representations as to the accuracy or completeness of the information contained herein and assumes no responsibility regarding the consequences of its use or for any printing errors.

Not being able to foresee the countless conditions to which our information and our product will be use, alone or in combination with other, our Company doesn't guarantee the applicability not even the suitability of the use that is done, therefore decline any responsibility for damage to customer or third parties. Drying is recommended.

Our products are intended for sale industrial and commercial customers. It is the customer's responsibility to inspect and test our product in order to satisfy himself as to the suitability of the products for the customer's particular purpose. The customer is also responsible for the appropriate, safe and legal use, processing and handling of our products.

A.D. Compound S.p.a. Via Meucci, 2 28066 Galliate (NO) Tel. +39 0321 866834 Fax +39 0321 866850 www.adcompound.com

Sede legale: Via Larga, 6 20122 Milano (MI) C.F.-P.I. 02253490128 C.S. €4.250.000,00 i.v. Registro imprese: Milano n.02253490128 REA n. 1815199

IDM 8.5.02